

Supplementary Information

Replacing Ag^{TS}SCH₂-R with Ag^{TS}O₂C-R in EGaIn-Based Tunneling Junctions Does Not Significantly Change Rates of Charge Transport

Kung-Ching Liao,¹ Hyo Jae Yoon,¹ Carleen M. Bowers,¹ Felice C. Simeone,¹ and George M.

Whitesides^{1,2,3*}

¹Department of Chemistry and Chemical Biology, Harvard University,
12 Oxford Street, Cambridge, Massachusetts 02138 United States,

²Wyss Institute for Biologically Inspired Engineering, Harvard University,
60 Oxford Street, Cambridge, Massachusetts 02138 United States, and

³Kavli Institute for Bionano Science & Technology, Harvard University,
29 Oxford Street, Massachusetts 02138 United States

*Corresponding author, email: gwhitesides@gmwgroup.harvard.edu

Contents

Experimental Details	1
Table S1	3
References	4

Experimental Details

Materials. All monolayer precursors: *n*-alkanoic acids ($\text{CH}_3(\text{CH}_2)_{2n}\text{CO}_2\text{H}$, $n = 1 - 8$), oligo(phenylene)carboxylic acids ($\text{HO}_2\text{C}(\text{C}_6\text{H}_4)_n\text{H}$, $n = 1 - 3$), and *n*-alkanethiols ($\text{CH}_3(\text{CH}_2)_{2n}\text{CH}_2\text{SH}$, $n = 1 - 8$) are commercially available ($\geq 96\%$, Sigma-Aldrich), and all carboxylic acids were used as received. All organic solvents were analytical grade (99%, Sigma-Aldrich) and were used as supplied unless otherwise specified. All thiols used to make SAMs were purified by silica-gel column chromatography (using 15% ethyl acetate in hexane, and gravity elution). All purified alkanethiols were maintained under a N_2 atmosphere at $< 4^\circ\text{C}$. To ensure purity, all stored compounds were checked by ^1H NMR prior to use.

Template-Stripped Silver (Ag^{TS}) Substrates. Four hundred-nanometer thick Ag films were electron-beam evaporated onto a single-side polished n-doped silicon (Si) wafer with $\langle 111 \rangle$ orientation, and then attached to glass substrates using a photo-cured optical adhesive (Norland Optical Adhesive 61, Norland Products). The resulting Ag^{TS} films are ultrasmooth with an rms roughness of 0.5 nm. The low surface roughness significantly increases the yield of working junctions. Exact film preparation and characterization is detailed elsewhere.¹⁻³

Eutectic Gallium-Indium (EGaIn) Top Electrode. EGaIn is non-toxic, non-destructive, easy-to-handle, and commercially available (99.99%, Sigma-Aldrich). Upon exposure to air, EGaIn forms a thin, native gallium oxide film (Ga_2O_3 , with thickness about 0.7 nm) which facilitates the fabrication of different shapes with high precision in contact area ($50\ \mu\text{m}^2$ on average) and enhances the yield of working junctions.⁴⁻⁶ In this study, we used conical-shaped EGaIn top electrodes to form electrical contacts in junction measurements.^{4, 5, 7}

Monolayer Preparation. The preparation of SAMs of *n*-alkanoates and of *n*-alkanethiolates on Ag follows published procedures;⁷⁻¹¹ in brief, freshly prepared Ag^{TS} substrates were introduced

into the solution of monolayer precursor for 3 hours (1mM of each of the *n*-alkanoic acids in hexadecane or *n*-alkanethiols in toluene). The preparation of SAMs of oligophenylene carboxylates follows the reports published by Tao and coworkers.^{12, 13} Most of the SAM-bound Ag substrates emerged dry from the solution, but surfaces coated with shorter alkane-SAMs or aromatic SAMs emerged wet. We rinsed these substrates three times with anhydrous hexane/THF or toluene and dried these under a gentle stream of nitrogen.

Junction Measurements. These measurements were performed in ambient conditions, using conical EGaIn top electrodes to make electrical contacts to SAM-bonded Ag substrates.^{5-7, 14} In order to extract the current density (J , in A/cm^2), the EGaIn contact area ($50 \pm 10 \mu m^2$) was determined from the optically measured diameter. For each monolayer, at least 430 $J-V$ curves were measured (3 junctions made by a fresh EGaIn tip, 21 traces measured on a junction) from 3 – 4 different substrates. The $J(V)$ measurements were collected in a voltage scan mode between +0.5 and -0.5 V, back and forth ($0 V \rightarrow +0.5 V \rightarrow 0 V \rightarrow -0.5 V \rightarrow 0 V$), in steps of 0.05 V with a 0.02 second delay between scans.^{5-7, 10, 14}

Table S1. Summary of geometric information for SAMs of *n*-alkanethiolates,¹⁵⁻¹⁷ *n*-alkanoates,^{9, 18, 19} and oligophenylene carboxylates^{12, 13} on Ag (111). The calculation of molecular footprint is based on the lattice spacing and SAM overlayer.

	<i>n</i> -alkanethiolates	<i>n</i> -alkanoates	oligophenylene carboxylates
Tilt angle (°)	11-13	15-25	0
Cell	($\sqrt{7} \times \sqrt{7}$)R10.9°	<i>p</i> (2x2) ^a	<i>p</i> (2x2) ^a
Lattice spacing (Å)	4.4 ^b	5.8	10
Molecular footprint (Å ²)	6	6	18

^aOverlayer on Ag; ^bNearest neighbor spacing.

References

1. Weiss, E.A. *et al.* Si/SiO₂-Templated Formation of Ultraflat Metal Surfaces on Glass, Polymer, and Solder Supports: Their Use as Substrates for Self-Assembled Monolayers. *Langmuir* **23**, 9686-9694 (2007).
2. Thuo, M.M. *et al.* Odd–Even Effects in Charge Transport across Self-Assembled Monolayers. *J. Am. Chem. Soc.* **133**, 2962-2975 (2011).
3. Weiss, E.A. *et al.* Influence of Defects on the Electrical Characteristics of Mercury-Drop Junctions: Self-Assembled Monolayers of n-Alkanethiolates on Rough and Smooth Silver. *J. Am. Chem. Soc.* **129**, 4336-4349 (2007).
4. Chiechi, R.C., Weiss, E.A., Dickey, M.D. & Whitesides, G.M. Eutectic Gallium–Indium (EGaIn): A Moldable Liquid Metal for Electrical Characterization of Self-Assembled Monolayers. *Angew. Chem. Int. Ed.* **47**, 142-144 (2008).
5. Nijhuis, C.A., Reus, W.F., Barber, J.R. & Whitesides, G.M. Comparison of SAM-Based Junctions with Ga₂O₃/EGaIn Top Electrodes to Other Large-Area Tunneling Junctions. *J. Phys. Chem. C* **116**, 14139-14150 (2012).
6. Cademartiri, L. *et al.* Electrical Resistance of Ag^{TS}-S(CH₂)_n-CH₃//Ga₂O₃/EGaIn Tunneling Junctions. *J. Phys. Chem. C* **116**, 10848-10860 (2012).
7. Simeone, F.C. *et al.* Defining Injection Current and Effective Contact Area for EGaIn-based Molecular Tunnel Junctions. *Submitted* (2013).
8. Bain, C.D. *et al.* Formation of monolayer films by the spontaneous assembly of organic thiols from solution onto gold. *J. Am. Chem. Soc.* **111**, 321-335 (1989).
9. Tao, Y.T. Structural comparison of self-assembled monolayers of n-alkanoic acids on the surfaces of silver, copper, and aluminum. *J. Am. Chem. Soc.* **115**, 4350-4358 (1993).
10. Yoon, H.J. *et al.* The Rate of Charge Tunneling through Self-Assembled Monolayers Is Insensitive to Many Functional Group Substitutions. *Angew. Chem. Int. Ed.* **51**, 4658-4661 (2012).
11. Thuo, M.M. *et al.* Replacing –CH₂CH₂– with –CONH– Does Not Significantly Change Rates of Charge Transport through Ag^{TS}-SAM//Ga₂O₃/EGaIn Junctions. *J. Am. Chem. Soc.* **134**, 10876-10884 (2012).
12. Hsu, M.-H. *et al.* H₂S-Induced Reorganization of Mixed Monolayer of Carboxylic Derivatives on Silver Surface. *Langmuir* **20**, 3641-3647 (2004).

13. Tao, Y.T., Lee, M.T. & Chang, S.C. Effect of biphenyl and naphthyl groups on the structure of self-assembled monolayers: packing, orientation, and wetting properties. *J. Am. Chem. Soc.* **115**, 9547-9555 (1993).
14. Reus, W.F. *et al.* Statistical Tools for Analyzing Measurements of Charge Transport. *J. Phys. Chem. C* **116**, 6714-6733 (2012).
15. Chang, S.-C., Chao, I. & Tao, Y.-T. Structure of Self-Assembled Monolayers of Aromatic-Derivatized Thiols on Evaporated Gold and Silver Surfaces: Implication on Packing Mechanism. *J. Am. Chem. Soc.* **116**, 6792-6805 (1994).
16. Laibinis, P.E. *et al.* Comparison of the structures and wetting properties of self-assembled monolayers of n-alkanethiols on the coinage metal surfaces, copper, silver, and gold. *J. Am. Chem. Soc.* **113**, 7152-7167 (1991).
17. Kawasaki, M. & Iino, M. Self-Assembly of Alkanethiol Monolayers on Ag–Au(111) Alloy Surfaces. *J. Phys. Chem. B* **110**, 21124-21130 (2006).
18. Tao, Y.-T., Hietpas, G.D. & Allara, D.L. HCl Vapor-Induced Structural Rearrangements of n-Alkanoate Self-Assembled Monolayers on Ambient Silver, Copper, and Aluminum Surfaces. *J. Am. Chem. Soc.* **118**, 6724-6735 (1996).
19. Lin, S.-Y. *et al.* Structures of Self-Assembled Monolayers of n-Alkanoic Acids on Gold Surfaces Modified by Underpotential Deposition of Silver and Copper: Odd–Even Effect. *Langmuir* **18**, 5473-5478 (2002).